





Tungaloy Report No. 524-G

High speed face milling cutter

for finishing aluminum







ACCELERATED MACHINING







Super high density PCD cutter

with innovative insert clamp design for quick and easy insert setting



Super high density cutter for efficient finishing of aluminum

Extremely high number of PCD cutting edges

Ensures machining efficiency

22 inserts per ø100 mm cutter diameter. Allows a cutting speed of 3,000 m/min or higher.



Unique axial adjusting mechanism - Cam Adjust

A single key wrench is all it takes from mounting the inserts to fine-adjusting for precision, saving a great amount of presetting work. Setting range: 1 mm



Internal coolant in each pocket

Coolant is directed to the cutting edge, facilitating smooth chip evacuation

Steel body

the cutter body is made of durable steel


Extremely high balancing quality for high speed milling

G6.3 under ISO1940/1

Safety measures for high speed milling

Safety insert lock against centrifugal force

Inserts are securely retained in place, preventing them from being dislocated by centrifugal force during high speed milling



Wedge shape design prevents the insert from breaking off the seat induced by centrifugal inertia force.

Note: Do not exceed the maximum rotation (n \max) inscribed on the cutter body.

Cutter diameter (mm)	Max num. of teeth	Max. rotation number (min ⁻¹)	Cutter weight (kg)
50	8	20,000	0.86
63	10	19,000	0.53
80	16	17,000	1.18
100	22	15,000	1.66
125	26	14,000	3.44
160	34	12,000	5.15

CamAdjust system - innovative insert axial adjusting mechanism

- The same key is used for mounting and adjusting the inserts
- The key wrench is operated in a single direction making insert adjustment easy on the pre-setter
- Significantly reduced insert setting time


TORX bit for clamping insert



Eccentric cam for adjusting axial runout



Special key wrench with adjusting cam





Insert variations


Standard insert with built-in deburrer (YDEN0603PDFR-D, YDEN0603PDSR-D)

- Double-angled cutting edge for effective chip splitting
- Burr formation is significantly minimized by the cutting edge's chip thinning effect at the exit
- Built-in wiper geometry for better surface finishing



Standard insert with edge preparation (YDEN0603PDSR-D)


For cutting gates or greater depths of cut



Deburring insert - Tungaloy's exclusive insert design


(YDEN0603PDFR-BD)

Use with standard inserts for enhanced burr-free machining



Wiper insert - for superior surface finishing (YDEN0603PDFR-WD)


Use with standard inserts to improve the surface finishing quality. Number of wiper inserts on the cutter may depend on the feed rate.



CUTTING PERFORMANCE

Reduced burr formation

2 types of deburring inserts for burr-free milling



Cutter : TPYD06J080B25.4R16 (Ø = 80 mm, z = 16)
Insert : YDEN0603PDFR-D DX110 (Standard insert)
: YDEN0603PDFR-BD DX110 (Deburring insert)

Workpiece : A1100 (30x100 mm) Cutting speed : Vc = 2,513 m/min Number of revolutions : n = 10,000 min⁻¹ Feed per tooth : fz = 0.1 mm/t

Feed speed : Vf = 16,000 m/min (Standard insert)


: Vf = 8,000 m/min (Standard and deburring insert)

 $\begin{array}{ll} \mbox{Insert runout} & : < 1 \ \mu m \\ \mbox{Depth of cut} & : ap = 0.5 \ mm \\ \mbox{Depth of width} & : ae = 30 \ mm \\ \mbox{Coolant} & : \mbox{Wet} \end{array}$

Machining : Face milling (on center)
Machine : Vertical M/C, BT40

Better surface roughness

Wiper inserts improve surface roughness



Cutter : TPYD06J080B25.4R16 (Ø = 80 mm, z = 16)
Insert : YDEN0603PDFR-D DX110 (Standard insert)

: YDEN0603PDFR-WD DX110 (Wiper insert) : A1100 (30x100 mm)

Workpiece : A1100 (30x100 mm)


Cutting speed : Vc = 2,513 m/min

Number of revolutions : n = 10,000 min⁻¹

Feed per tooth : fz = 0.1 mm/t

Feed speed : Vf = 16,000 m/min

Machining : Face milling (on center)
Machine : Vertical M/C, BT40






CUTTING PERFORMANCE

Strong cutting edge

Optimized edge preparation ensures machining security during heavy interrupted cutting



 $\begin{tabular}{lll} Cutter & : TPYD06J100B31.7R22 \ (\emptyset = 100 \ mm, \ z = 1) \\ Insert & : YDEN0603PDSR-D \ DX110 \ (with edge \ preparation) \\ \end{tabular}$

Workpiece : AC4C-T6 (150 x 200 mm with 70 holes)

Cutting speed : Vc = 3,141 m/minNumber of revolutions : $n = 10,000 \text{ min}^{-1}$ Feed per tooth : fz = 0.09 mm/tInsert runout : < 1 µmDepth of cut : ap = 0.2 mmDepth of width : ae = 75 mm

Coolant : Wet

Machining : Face milling (down cut)
Machine : Vertical M/C, BT40

After 130 min.



Mounting of deburring inserts

To make the best of the cutter's deburring ability, make sure to place a deburring insert immediately behind every standard insert on the cutter. Please note that, since a deburring insert has no cutting edge on the periphery, the effective cutting edges of the cutter will be divided by 2.

Example:

For \emptyset 100 mm cutter with Z = 22, number of effective cutting edges would be Z = 11. (standard inserts x 11 and deburring inserts x 11)


The order of insert installation is as follows: Standard → Deburring → Standard → Deburring...




Proper cutting edge setting

- For the best surface finishing results, wiper insert's (-WD) cutting edge should be set 0.06 mm higher than that of the standard insert's (-D). For deburring inserts (-BD), set 0.2 mm higher than that of the standard insert (-D).
- Effective cutter diameter will vary in accordance with wiper insert (-WD) or deburring insert (-BD) dimensions. Refer to the table below for an effective cutter diameter in each specific case.

Cutter		mm)	
diameter (mm)	Standard (-D) only	Standard (-D) and wipers (-WD)	Standard (-D) and deburrers (-BD)
50	50	49.4	43.4
63	63	62.4	56.4
80	80	79.4	73.4
100	100	99.4	93.4
125	125	124.4	118.4
160	160	159.4	153.4








TPYD06

Face milling cutter for non-ferrous applications, bore type, with PCD inserts

 $GAMP = +9^{\circ}, GAMF = +4^{\circ}$





Designation	АРМХ	DC	DCX	CICT	DCSFMS	LF	DCON	CBDP	KWW	b	WT(kg)	Air hole	RPMX(min ⁻¹)	Insert
TPYD06M063B22.0R10	4.5	63	65	10	45	40	22	20	10.4	6.3	0.57	with	19,000	YDEN0603
TPYD06M080B27.0R16	4.5	80	82	16	60	50	27	22	12.4	7	1.24	with	17,000	YDEN0603
TPYD06J080B25.4R16	4.5	80	82	16	60	50	25.4	26	9.5	6	1.26	with	17,000	YDEN0603
TPYD06M100B32.0R22	4.5	100	102	22	70	50	32	25	14.4	8	1.78	with	15,000	YDEN0603
TPYD06J100B31.7R22	4.5	100	102	22	70	50	31.7	32	12.7	8	1.76	with	15,000	YDEN0603
TPYD06M125B40.0R26	4.5	125	127	26	90	60	40	32	16.4	9	3.48	with	14,000	YDEN0603
TPYD06J125B38.1R26	4.5	125	127	26	90	60	38.1	38	15.9	10	3.56	with	14,000	YDEN0603
TPYD06M160B40.0R34	4.5	160	162	34	90	60	40	32	16.4	9	5.20	with	12,000	YDEN0603
TPYD06J160B38.1R34	4.5	160	162	34	90	60	38.1	38	15.9	10	5.29	with	12,000	YDEN0603

SPARE PARTS								
Designation	Insert locking wedge	Wedge fixing screw	Adjusting cam	Torx bit	Cam tightening screw	Wrench	Grip	Shell locking bolt
TPYD06M063B22.0R10	WF875N	DS-5T	AJC08	BLDT10/S7-A	SSHM4-4	P-2	H-TB2W	CM10X30H
TPYD06*080B2*.*R16	WF875N	DS-5T	AJC08	BLDT10/S7-A	SSHM4-4	P-2	H-TB2W	CM12X30H
TPYD06*100B32.0R22	WF875N	DS-5T	AJC08	BLDT10/S7-A	SSHM4-4	P-2	H-TB2W	CM16X40H
TPYD06*100B31.7R22	WF875N	DS-5T	AJC08	BLDT10/S7-A	SSHM4-4	P-2	H-TB2W	TMBA-M16H
TPYD06*125B**.*R26	WF875N	DS-5T	AJC08	BLDT10/S7-A	SSHM4-4	P-2	H-TB2W	TMBA-M20H
TPYD06*160B**.*R34	WF875N	DS-5T	AJC08	BLDT10/S7-A	SSHM4-4	P-2	H-TB2W	TMBA-M20H

ACCELERATED MACHINING

with

20,000

0.57

YDEN0603...

EPYD06

EPYD06M050C32.0R08 4.5

52

Face milling cutter for non-ferrous applications, shank type, with PCD inserts

GAMP = +9°, GAMF = +4°

APMX

Designation APMX

DC DCX CICT DCONMS LF LH LS WT(kg) Air hole RPMX(min-1) Insert



120

40



INSERT

YDEN0603PD(F/S)R-D YDEN0603PDFR-WD INSL R400 ₹ YDEN0603PDFR-BD INSL R400 Steel Stainless Cast iron Non-ferrous * Superalloys ★ : First choice H Hard materials PCD

Note: Tungaloy provides refurbishing service of PCD inserts upon request.

APMX

4.5

4.5

3.1 Package quantity = 1 pc. per box

S

3.1

BS

22

2.2

LE

6.5

6.5

Managing re-ground inserts

Designation

YDEN0603PDFR-D

YDEN0603PDSR-D

YDEN0603PDFR-WD

YDEN0603PDFR-BD

- To maintain its minimum insert capability, re-grinding over 0.8 mm off the original cutting edge profile is not provided.

Edge

prep.


Without

With

Without

Without

- Regrinding will change the dimension of the wiper edge and may affect the surface finishing quality.
- Used PCD inserts are reground as a batch from the same cutter in order to maintain the dimensional uniformity of all inserts in the same batch.
- When inserts from a different batch is accidently mixed, the cutter balance may collapse, and the tool or machine may fracture.
- Re-check the cutter diameter, as needed, after re-grinding inserts are mounted to offset the tool.



W1 INSL

12.7

12.7 3.1

12.8 3.1

12.9

9.5


9.5

STANDARD CUTTING CONDITIONS

ISO	Workpiece materials	Grades	Designation	Cutting speed Vc (m/min)	Feed per tooth fz (mm/t)
	Cast aluminum alloy / Die-cast (Si < 13%)	DX110	YDEN0603PDFR-D	500 - 4,000	0.05 - 0.20
N	Cast aluminum alloy / Die-cast (Si > 13%)	DX110	YDEN0603PDFR-D	200 - 800	0.05 - 0.20
	Aluminum alloy	DX110	YDEN0603PDFR-D	500 - 4,000	0.05 - 0.20
	Copper alloy	DX110	YDEN0603PDFR-D	200 - 500	0.05 - 0.20

- The values in the above list are of standard recommendations and may require adjustments in consideration with cutting depths and/or workpiece/machine rigidity.
- Use wiper inserts (-WD) for better surface requirements and deburring inserts (-BD) to remove burrs.
- Always use wet cutting (emulsion coolant) for machining aluminum or copper alloys.

APPLICATION RANGE



Cutter : TPYD06J080B25.4R16 (\emptyset = 80 mm, z = 16)

Insert : YDEN0603PDFR-D DX110

Workpiece material : ADC12

Cutting speed : Vc = 2,513 m/min

Coolant : Wet

Machine : Vertical M/C, BT40, 18.5 kW



INSERT SETTING PROCEDURE

Mounting the inserts

Place the insert in the pocket and LIGHTLY tighten the screw at 1 N·m(0.74 ft-lb).


Do not fully tighten the screw at this point. Note: Press the insert firmly to the pocket while clamping to eliminate the gap





2 House to utilize the key

The recessed part of the cam should be placed on the insert bottom. Make sure to place the cam all the way in.



Adjusting the axial height

Place the adjusting cam in the hole located at the bottom of the pocket. Make sure that the cam is in contact with the insert bottom. Adjust the insert axial height by rotating the cam in the CW direction to gradually increase the axial measure. Stop when it reaches 30-40 µm just below the desired position. Then, slightly rotate the cam in the CCW direction before removing the cam from the cutter body.



4 Tighten the insert clamping screws

Firmly tighten the insert clamping screws at 3.5 N·m (2.58 ft-lb). In order to prevent the body deformation by tightening, it is recommended that the final tightening is done by alternately. (e.g. For Ø100-z22, 1,3,5,7...21, then 2,4,6,8,...22). For the best balanced insert installation, repeat this tightening procedure for every other insert until all inserts are securely fixed.





Final adjustments

For the final axial adjustment, instead of setting the insert height close to the target position, set so that it reaches approximately 8 μm above the target. Slightly rotate the cam CCW to remove the key off the body. The insert will go down by 8 μm to the target height when the cam is removed.

The inserts are recommended to set to $< 5~\mu m$ axially in relation to one another.

PRACTICAL EXAMPLES

Insert YDEN0603PDFR-D DX110 High pressure aluminum die cast (ADC12) Workpiece material Cutting speed: Vc (m/min) Feed per tooth: fz (mm/t) Feed speed: Vf (mm/min) Depth of cut: ap (mm) Width of cut: ae (mm) Machining Coolant YDEN0603PDFR-D DX110 High pressure Physical	3,142 0.09 20,000 4.5/1.5 10 - 70 Face milling Wet (Internal) Vertical M/C, BT40 2.5 times!
Workpiece material Cutting speed: Vc (m/min) Feed per tooth: fz (mm/t) Feed speed: Vf (mm/min) Depth of cut: ap (mm) Width of cut: ae (mm) Machining Coolant DX110 High pressure aluminum die cast (ADC12) High pressure 10 10 11 12,011 12,800 12,800 14 14 15 16 17 18 18 18 18 18 18 18 18 18 18 18 18 18	DX110 Irre aluminum die cast (ADC12) 3,142 0.09 20,000 4.5/1.5 10 - 70 Face milling Wet (Internal) Vertical M/C, BT40
Workpiece material Cutting speed: Vc (m/min) Feed per tooth: fz (mm/t) Feed speed: Vf (mm/min) Depth of cut: ap (mm) Width of cut: ae (mm) Machining Coolant High pressure aluminum die cast (ADC12) High pressure 1. 1. 2,011 Feed per tooth: fz (mm/t) 0.1 Feed speed: Vf (mm/min) 12,800 Depth of cut: ap (mm) 4/1 Width of cut: ae (mm) Face milling Coolant Wet (External)	3,142 0.09 20,000 4.5/1.5 10 - 70 Face milling Wet (Internal) Vertical M/C, BT40
Workpiece material Cutting speed: Vc (m/min) Feed per tooth: fz (mm/t) Feed speed: Vf (mm/min) Depth of cut: ap (mm) Width of cut: ae (mm) Machining Coolant High pressure aluminum die cast (ADC12) High pressure 1. 1. 2,011 Feed per tooth: fz (mm/t) 0.1 Feed speed: Vf (mm/min) 12,800 Depth of cut: ap (mm) 4/1 Width of cut: ae (mm) Face milling Coolant Wet (External)	3,142 0.09 20,000 4.5/1.5 10 - 70 Face milling Wet (Internal) Vertical M/C, BT40
Workpiece material Cutting speed: Vc (m/min) Feed per tooth: fz (mm/t) Feed speed: Vf (mm/min) Depth of cut: ap (mm) Width of cut: ae (mm) Machining Coolant Wet (External)	3,142 0.09 20,000 4.5/1.5 10 - 70 Face milling Wet (Internal) Vertical M/C, BT40
Feed per tooth: fz (mm/t)	0.09 20,000 4.5/1.5 10 - 70 Face milling Wet (Internal) Vertical M/C, BT40
Feed per tooth: fz (mm/t)	20,000 4.5/1.5 10 - 70 Face milling Wet (Internal) Vertical M/C, BT40
Feed speed: Vf (mm/min) 12,800	20,000 4.5/1.5 10 - 70 Face milling Wet (Internal) Vertical M/C, BT40
Depth of cut: ap (mm)	4.5/1.5 10 - 70 Face milling Wet (Internal) Vertical M/C, BT40
Width of cut: ae (mm) 5 - 20	10 - 70 Face milling Wet (Internal) Vertical M/C, BT40
Machining Face milling Coolant Wet (External) Machine Vertical M/C, BT50	Face milling Wet (Internal) Vertical M/C, BT40 Productivity
Coolant Wet (External) Machine Vertical M/C, BT50	Wet (Internal) Vertical M/C, BT40 Productivity
Machine Vertical M/C, BT50	Vertical M/C, BT40 Productivity
**************************************	Productivity
	Competitor byed by 2.5x thanks to super tter design.
Workpiece type Cam housing	Cylinder head
	PYD06 body (ø75 mm, z = 15)
	/DEN0603PDSR-D
Grade DX110	DX110
Workpiece material High pressure aluminum die cast (ADC12) Cast	aluminum alloy (AC2B)
<u>α</u> Cutting speed: Vc (m/min) 1,916	990
Cutting speed: Vc (m/min) 1,916 Feed per tooth: fz (mm/t) 0.11	0.04
Feed speed: Vf (mm/min) 11,400	2,849
Feed speed: Vf (mm/min) 11,400 Depth of cut: ap (mm) 0.5 Width of cut: ae (mm) - 5	0.5
Width of cut: ae (mm) -5	- 70
Machining Face milling Coolant Wet (Internal) Wether Machine Service Machine	Face milling
Coolant Wet (Internal)	Wet (Internal)
Machine Vertical M/C, BT30	pecialized machine
Results Tool life 3 times! Quantification of the state	Tool life 27 times! Competitor DX110 PCD grade dramatically

Tungaloy Corporation (Head office)

11-1 Yoshima-Kogyodanchi lwaki-city, Fukushima, 970-1144 Japan Phone: +81-246-36-8501 Fax: +81-246-36-8542 www.tungaloy.co.jp

Tungaloy America, Inc.

Tungaloy Canada

432 Elgin St. Unit 3 Brantford, Ontario N3S 7P7, Canada Phone: +1-519-758-5779 Fax: +1-519-758-5791

Tungaloy de Mexico S.A.

Tungaloy do Brasil Ltda.

Avd. Independencia N4158 Residencial Flora 13280-000 Vinhedo, São Paulo, Brasil Phone: +55-19-38262757 Fax: +55-19-38262757

Tungaloy Germany GmbH

An der Alten Ziegelei 1 D-40789 Monheim, Germany Phone: +49-2173-90420-0 Fax: +49-2173-90420-19

Tungaloy France S.A.S.

ZA Courtaboeuf - Le Rio 1 rue de la Terre de feu F-91952 Courtaboeuf Cedex, France Phone: +33-1-6486-4300 Fax: +33-1-6907-7817 www.tungaloy.fr

Tungaloy Italia S.r.I.

Via E. Andolfato 10 I-20126 Milano, Italy Phone: +39-02-252012-1 Fax: +39-02-252012-65 www.tungaloy.it

Tungaloy Czech s.r.o.

Tungaloy Ibérica S.L.

C/Miquel Servet, 43B, Nau 7 Pol. Ind. Bufalvent ES-08243 Manresa (BCN), Spain Phone: +34 93 113 1360 Fax: +34 93 876 2798

Tungaloy Scandinavia AB

Tungaloy Rus, LLC

115432, Moscow, Andropov Avenue, 18, building 7, 11th floor (office 3). Metro station "Technopark". Business center «I-Land». Phone: +7-499-683-01-80/81

Tungaloy Polska Sp. z o.o.

Tungaloy U.K. Ltd

The Technology Centre, Wolverhampton Science Park Glaisher Drive, Wolverhampton West Midlands WV10 9RU, UK Phone: +44 121 4000 231 Fax: +44 121 270 9694 www.tungaloy.com/uk salesinfo@tungaloyuk.co.uk

Tungaloy Hungary Kft

Erzsébet királyné útja 125 H-1142 Budapest, Hungary Phone: +36 1 781-6846 Fax: +36 1 781-6866 www.tungaloy.com/hu info@tungaloytools.hu

Tungaloy Turkey

Dudullu, OSB 4. Cad No:4 34776 Umraniye Istanbul, TURKEY Phone: +90 216 540 04 67 Fax: +90 216 540 04 87 www.tungaloy.com.tr

Tungaloy Benelux b.v.

Tjalk 70 NL-2411 NZ Bodegraven, Netherlands Phone: +31 172 630 420 Fax: +31 172 630 429 www.tungaloy-benelux.com

Tungaloy Croatia

Ulica bana Josipa Jelačića 87, 10430 Samobor Phone: +385 1 3326 604 Fax: +385 1 3327 683 www.tungaloy.hr

Tungaloy Cutting Tool (Shanghai) Co.,Ltd.

Rm No 401 No 88 Zhabei Jiangchang No 3 Rd Shanghai 200436, China Phone: +86-21-3632-1880 Fax: +86-21-3621-1918

Tungaloy Cutting Tool (Thailand) Co.,Ltd.

Interlink tower 4th FI. 1858/5-7 Bangna-Trad Road km.5 Bangna, Bangna, Bangkok 10260 Thailand Phone: +66-2-751-5711 Fax: +66-2-751-5715 www.tungaloy.co.th

Tungaloy Singapore (Pte.), Ltd.

62 Ubi Road 1, #06-11 Oxley BizHub 2 Singapore 408734 Phone: +65-6391-1833 Fax: +65-6299-4557

Tungaloy Vietnam

LE 04-38, Lexington Residence 67 Mai Chi Tho, Dist. 2, Ho Chi Minh City, Vietnam Phone: +84-8-37406660 Fax: +84-8-37406662 www.tungaloy.com/sg

Tungaloy India Pvt. Ltd.

Indiabulls Finance Centre, Unit # 902-A, 9th Floor, Tower 1, Senapati Bapat Marg, Elphinstone Road (West), Mumbai -400013, India Phone: +91-22-6124-8804 Fax: +91-22-6124-8899

Tungaloy Korea Co., Ltd

#1312, Byucksan Digital Valley 5-cha Beotkkot-ro 244, Geumcheon-gu 153-788 Seoul, Korea Phone: +82-2-2621-6161 Fax: +82-2-6393-8952 www.tungaloy.com/kr

Tungaloy Malaysia Sdn Bhd

50 K-2, Kelana Mall, Jalan SS6/14 Kelana Jaya, 47301 Petaling Jaya, Selangor Darul Ehsan

Tungaloy Australia Pty Ltd

PO Box 2232, 68/1470 Ferntree Gully Road, Knoxfield Victoria 3180, Australia Phone: +61-3-9755-8147 Fax: +61-3-9755-6070 www.tungaloy.com.au

PT. Tungaloy Indonesia



www.tungaloy.com follow us at:

facebook.com/tungaloyjapan twitter.com/tungaloyjapan www.youtube.com/tungaloycorporation



AS9100 Certified 78006 2015.11.04 ISO14001 Certified EC97J1123 1997.11.26

Distributed by:















