

RECOMMENDED INSERTS

ISO	Workpiece materials	First choice	High feed	High speed	Troubleshooting			
					Chipping resistance	Wear resistance	Surface finish	Chip control
P	Low carbon steel (C ≤ 0.3%)	DS, AH6030	-	-	DS, AH725	-	DW, AH6030	DG, AH725
	Carbon steel (C > 0.3%) Alloy steels	DJ, AH6030	DW, AH6030	DJ, AH9030	DW, AH725	DJ, AH9030	DW, AH6030	-
	Low alloy steel	DS, AH6030	-	-	DS, AH725	-	DW, AH6030	-
M	Stainless steel	DS, AH6030	-	-	DS, AH725	-	DW, AH6030	DG, AH725
K	Grey cast iron	DJ, AH9030	DW, AH9030	DJ, T1115	DW, AH725	-	DW, AH9030	-
	Ductile cast iron	DJ, AH9030	DW, AH9030	-	DW, AH725	-	DW, AH9030	-
N	Aluminium alloys	DJ, AH725	DW, AH725	DS, AH6030	-	-	DW, AH725	DG, AH725
S	Titanium alloys Heat-resistant alloys	DS, AH6030	-	-	DW, AH725	-	DW, AH725	DG, AH725
H	Hardened steel	DJ, AH9030	DW, AH9030	-	DW, AH725	-	DW, AH9030	-

STANDARD CUTTING CONDITIONS

ISO	Workpiece materials	Cutting speed Vc (m/min)	Series L/D	Feed: f (mm/rev)				
				ø12.5 ~ ø14.5	ø15 ~ ø17	ø17.5 ~ ø26	ø27 ~ ø32	ø33 ~ ø54
P	Low carbon steel (C ≤ 0.3%) SS400, SM490, S25C, etc. (St42-1, St52-3, C25, etc.)	160 - 320	2D, 3D	0.02 - 0.06	0.02 - 0.06	0.04 - 0.1	0.04 - 0.1	0.04 - 0.1
			4D, 5D	0.02 - 0.06	0.02 - 0.06	0.04 - 0.1	0.04 - 0.1	0.04 - 0.1
	Carbon steel (C > 0.3%) S45C, S55C, etc. (C45, C55, etc.)	80 - 250	2D, 3D	0.04 - 0.1	0.04 - 0.12	0.06 - 0.13	0.06 - 0.15	0.08 - 0.18
			4D, 5D	0.04 - 0.08	0.04 - 0.08	0.06 - 0.1	0.06 - 0.12	0.08 - 0.14
M	Low alloy steel SCM415, etc.	160 - 250	2D, 3D	0.04 - 0.08	0.04 - 0.08	0.06 - 0.12	0.06 - 0.12	0.06 - 0.14
			4D, 5D	0.04 - 0.08	0.04 - 0.08	0.06 - 0.12	0.06 - 0.12	0.06 - 0.14
	Alloy steel SCM440, SCr420, etc. (42CrMo4, 20Cr4, etc.)	80 - 200	2D, 3D	0.04 - 0.1	0.04 - 0.12	0.06 - 0.13	0.06 - 0.15	0.08 - 0.18
			4D, 5D	0.04 - 0.08	0.04 - 0.08	0.06 - 0.1	0.06 - 0.12	0.08 - 0.14
K	Stainless steel (Austenitic) SUS304, SUS316, etc. (X5CrNi18-9, X5CrNiMo17-12-2, etc.)	100 - 200	2D, 3D	0.02 - 0.08	0.02 - 0.08	0.04 - 0.1	0.04 - 0.12	0.04 - 0.12
			4D, 5D	0.02 - 0.08	0.02 - 0.08	0.04 - 0.1	0.04 - 0.12	0.04 - 0.12
	Stainless steel (Martensitic, Ferritic) SUS430, SUS416, etc. (X5CrNi18-9, X5CrNiMo17-12-2, etc.)	100 - 220	2D, 3D	0.02 - 0.08	0.02 - 0.08	0.04 - 0.1	0.04 - 0.12	0.04 - 0.12
4D, 5D			0.02 - 0.08	0.02 - 0.08	0.04 - 0.1	0.04 - 0.12	0.04 - 0.12	
N	Stainless steel (Precipitation hardening) SUS630, etc. (X5CrNiCuNb16-4, etc.)	80 - 120	2D, 3D	0.04 - 0.08	0.04 - 0.08	0.04 - 0.08	0.04 - 0.1	0.06 - 0.1
			4D, 5D	0.04 - 0.08	0.04 - 0.08	0.04 - 0.08	0.04 - 0.1	0.06 - 0.1
K	Grey cast iron FC250, etc. (GG25, etc.)	80 - 250	2D, 3D	0.06 - 0.12	0.06 - 0.12	0.06 - 0.15	0.06 - 0.18	0.08 - 0.2
			4D, 5D	0.06 - 0.1	0.06 - 0.1	0.06 - 0.12	0.06 - 0.14	0.08 - 0.16
S	Ductile cast iron FCD700, etc. (GGG70, etc.)	80 - 200	2D, 3D	0.04 - 0.12	0.04 - 0.12	0.06 - 0.15	0.06 - 0.18	0.08 - 0.2
			4D, 5D	0.04 - 0.1	0.04 - 0.1	0.06 - 0.12	0.06 - 0.14	0.08 - 0.16
N	Aluminium alloys A2017, ADC12, etc.	200 - 400	2D, 3D	0.1 - 0.12	0.1 - 0.15	0.15 - 0.2	0.15 - 0.2	0.15 - 0.25
			4D, 5D	0.08 - 0.12	0.08 - 0.12	0.12 - 0.16	0.12 - 0.16	0.12 - 0.2
S	Heat-resistant alloys Inconel 718, etc.	20 - 60	2D, 3D	0.04 - 0.08	0.04 - 0.08	0.04 - 0.1	0.04 - 0.1	0.04 - 0.1
			4D, 5D	0.04 - 0.08	0.04 - 0.08	0.04 - 0.1	0.04 - 0.1	0.04 - 0.1
H	Titanium alloys Ti-6Al-4V, etc.	40 - 120	2D, 3D	0.06 - 0.1	0.06 - 0.1	0.06 - 0.12	0.06 - 0.12	0.06 - 0.12
			4D, 5D	0.06 - 0.08	0.06 - 0.08	0.06 - 0.1	0.06 - 0.1	0.06 - 0.1
H	Hardened steel ≥ 40HRC	40 - 100	2D, 3D	0.04 - 0.08	0.04 - 0.08	0.04 - 0.1	0.04 - 0.1	0.04 - 0.1
			4D, 5D	0.04 - 0.08	0.04 - 0.08	0.04 - 0.08	0.04 - 0.08	0.04 - 0.08

STANDARD CUTTING CONDITIONS FOR DG TYPE CHIPBREAKER

ISO	Workpiece materials	Cutting speed Vc (m/min)	Series L/D	Feed: f (mm/rev)	
				ø27 ~ ø32	ø33 ~ ø54
P	Low carbon steel (C ≤ 0.3%) SS400, SM490, S25C, etc. (st42-1, St52-3, C25, etc.)	60 - 180	2D, 3D 4D, 5D	0.04 - 0.1	

- For small drill diameters, lower feed rate should be applied.
 - In case of workpiece materials with hardness of more than 40 HRC, the feed rate should be less than 50% of the recommended feed.
 - For difficult-to-cut materials, such as heat-resistant alloys, that generate high volume of cutting heat during machining, the cutting speed should be less than 20% of the recommended value for carbon steel.

- For high-feed machining with DW type chipbreaker, the feed rate should be approximately 1.5 times higher than the standard rate shown above.
 - High-speed machining applies to operation with the cutting speed more than 150 m/min.
 - When using DW type chipbreaker for troubleshooting, the operation should be within the range of standard cutting conditions.
 - DG type chipbreaker is suitable for large-sized machines with low-RPM spindle. If chattering occurs, the feed rate should be lowered.