

STANDARD CUTTING CONDITIONS

TPA/EPA/HPA

ISO	Workpiece materials	Hardness HB	Grades	Cutting speed <i>Vc</i> (m/min)				Feed per tooth: <i>fz</i> (mm/t)			
				T/E/HPA06	T/E/HPA10	T/EPA15	T/E/HPA06	T/E/HPA10	T/EPA15	T/EPA15	T/E/HPA10
P	Low carbon steel (SS400 / E275A, S15C / C15E4, etc.)	- 200	AH3135	100 - 220	100 - 250	100 - 250	0.05 - 0.15	0.08 - 0.2	0.08 - 0.25	0.08 - 0.15	-
	High carbon steel (S45C / C45, etc.)	200 - 300	AH3135	100 - 170	100 - 200	100 - 230	0.05 - 0.12	0.08 - 0.15	0.08 - 0.2	0.08 - 0.15	-
	Alloy steel (SCM440, etc. / 42CrMo4, etc.)	150 - 300	AH3135	100 - 170	100 - 200	100 - 230	0.05 - 0.12	0.08 - 0.15	0.08 - 0.2	0.08 - 0.15	-
	Tool steel (SKD61 / X40CrMoV5-1, etc.)	30 - 40 HRC	AH3135	100 - 120	100 - 150	100 - 180	0.05 - 0.12	0.08 - 0.15	0.08 - 0.2	0.08 - 0.15	-
M	Stainless steel (SUS304 / X5CrNi18-9, etc.)	-	AH3135	80 - 150	80 - 200	90 - 200	0.05 - 0.15	0.08 - 0.2	0.08 - 0.2	0.08 - 0.15	-
K	Grey cast iron (FC250 / GG25 / 250, etc.)	150 - 250	AH120 T1215	100 - 200 150 - 250	100 - 250 150 - 300	140 - 250 200 - 300	0.05 - 0.15 0.05 - 0.12	0.08 - 0.15 0.08 - 0.18	0.08 - 0.25 0.08 - 0.18	0.08 - 0.15 -	-
	Ductile cast iron (FCD450 / GGG45 / 450-10S, etc.)	150 - 250	AH120 T1215	80 - 150 100 - 200	80 - 200 130 - 250	110 - 200 150 - 250	0.05 - 0.15 0.05 - 0.12	0.08 - 0.2 0.08 - 0.15	0.08 - 0.25 0.08 - 0.18	0.08 - 0.15 -	-
N	Aluminium (Si < 13%)	-	KS05F	-	300 - 1000	-	-	-	-	-	0.08 - 0.22
	Aluminium (Si ≥ 13%)	-	KS05F	-	100 - 200	-	-	-	-	-	0.08 - 0.22
S	Titanium alloys (Ti-6Al-4V, etc.)	-	AH120	20 - 50	20 - 60	20 - 60	0.05 - 0.1	0.08 - 0.15	0.08 - 0.18	0.08 - 0.15	-
	Heat-resistant alloys (Inconel 718, etc.)	-	AH120	20 - 35	20 - 40	20 - 40	0.03 - 0.08	0.05 - 0.13	0.07 - 0.15	0.07 - 0.15	-

- When you use the NMJ chipbreaker, please set up the feed less than 0.15 mm/t.
- Remove excessive chip accumulation with an air blast.
- For the operation with depth of cut which varies (ex.casting skin) and machining of workpiece materials with interrupted surface, the feed per tooth (*fz*) should be set to the lower recommended value shown in the above table.

Cutting conditions maybe limited depending on machine power, workpiece rigidity, and spindle output. When the cutting width, depth, or overhang length is large, set *Vc* and *fz* to the lower recommended values and check the machine power and vibration.

TLA (Roughing type)

ISO	Workpiece materials	Hardness HB	Grades	Cutting speed <i>Vc</i> (m/min)				Feed per tooth: <i>fz</i> (mm/t)			
				TLA10	TLA15	TLA10	TLA15	TLA15	TLA10	TLA15	TLA10
P	Low carbon steel (SS400 / E275A, S15C / C15E4, etc.)	- 200	AH3135	100 - 250	100 - 250	0.08 - 0.18	0.08 - 0.22	0.08 - 0.15	-	-	-
	High carbon steel (S45C / C45, etc.)	200 - 300	AH3135	100 - 200	100 - 270	0.08 - 0.14	0.08 - 0.18	0.08 - 0.15	-	-	-
	Alloy steel (SCM440, etc. / 42CrMo4, etc.)	30 - 40 HRC	AH3135	100 - 150	100 - 180	0.08 - 0.14	0.08 - 0.18	0.08 - 0.15	-	-	-
	Stainless steel (SUS304 / X5CrNi18-9, etc.)	-	AH3135	80 - 200	90 - 200	0.08 - 0.15	0.08 - 0.18	0.08 - 0.15	-	-	-
K	Grey cast iron (FC250 / GG25 / 250, etc.)	150 - 250	AH120 T1215	100 - 250 150 - 250	140 - 250 150 - 250	0.08 - 0.18 0.08 - 0.15	0.08 - 0.25 0.08 - 0.18	0.08 - 0.15 -	-	-	-
	Ductile cast iron (FCD450 / GGG45 / 450-10S, etc.)	150 - 250	AH120 T1215	80 - 200 150 - 250	110 - 200 150 - 250	0.08 - 0.18 0.08 - 0.15	0.08 - 0.25 0.08 - 0.18	0.08 - 0.15 -	-	-	-
N	Aluminium (Si < 13%)	-	KS05F	300 - 1000	-	-	-	-	-	-	0.08 - 0.22
	Aluminium (Si ≥ 13%)	-	KS05F	100 - 200	-	-	-	-	-	-	0.08 - 0.22
S	Titanium alloys (Ti-6Al-4V, etc.)	-	AH120	20 - 60	20 - 60	0.08 - 0.15	0.08 - 0.18	0.08 - 0.15	-	-	-
	Heat-resistant alloys (Inconel 718, etc.)	-	AH120	20 - 40	20 - 40	0.05 - 0.13	0.07 - 0.15	0.07 - 0.15	0.07 - 0.15	-	-

- When using NMJ chipbreaker, please set up the feed not to exceed 0.15 mm/t.